



Sil 295 NB

Structural Glazing/Weatherseal
Neutral Cure Silicone Sealant

Technical Data Sheet

DESCRIPTION

BONDAFLEX Sil 295 is a versatile, structural glazing and weatherseal, one-component, non-sag, elastomeric, neutral cure silicone sealant. Meets the requirements of ASTM C-920, Type S, Grade NS, Class 50/50, Use NT, M, G, A, O; ASTM C-1184 Structural Silicone Sealant; TT-S-00230C, Type II, Class A; CAN/CGSB-19.13-M87, AAMA 802.3 Type II, AAMA 803.3, AAMA 805.2, AAMA 808.3 and California Air Resources Board 2003 requirements for Volatile Organic Compound content.

WHERE TO USE

Construction Application

- Structural glazing*
- Conventional glazing
- Perimeter sealing of windows, doors and skylights
- Panel stiffeners
- Expansion joints
- Precast expansion joints
- Unitized curtainwall assembly and field installation

Structure

- Buildings
- Schools
- Parking
- Plazas
- Stadiums
- Prisons

Location

- Vertical and horizontal
- Interior and exterior
- Above grade

Substrate

- Glass, aluminum, metal, tile, fiberglass, plastic, ceramic, masonry, concrete, brick, powder coated aluminum, fluoropolymer painted surfaces, vinyl, PVC, granite, limestone, marble and wood

FEATURES

- Versatile medium modulus
- Unaffected by most atmospheric conditions
- Non-staining
- Joint movement \pm 50%
- Excellent adhesion
- One-component
- Excellent gunnability in all temperatures
- 16 Bondaflex standard plus custom colors

BENEFITS

- Structural glazing and weatherseal applications with one product
- Extremely long service life
- Compatible with natural stone and masonry
- Excellent flexibility for dynamic joint movement
- Bonds to most substrates without priming including many Kynar® and anodized aluminum finishes
- Ready to use, labor cost reduction
- All season ease of application
- Matches a variety of substrates

TYPICAL PROPERTIES

Cured (21 days @ 77°F (25°C) and 50% RH)

		TEST METHOD
Movement Capability, %	+50 / 50	ASTM C-719
100% Modulus, psi (MPa)	55 (0.38)	ASTM D-412
Hardness, Shore A (Full Cure)	20	ASTM C-661
Tensile Strength, psi (MPa)	230 (1.59)	ASTM D-412
Elongation at Break, %	800	ASTM D-412
Peel Strength, pli	30 average	ASTM C-794
Accelerated Weathering 10,000 hrs.	No change	QUV Weatherometer
Staining	passes	ASTM C-1248

Uncured

Skin-Over Time	25 min.	MNA CTM
Tack-Free Time	50 min.	ASTM C-679
Cure Rate	1/8 inch/24 hrs.	MNA CTM
Extrusion Rate g/min 1/8" orifice @ 90 psi	150	ASTM C-1183 modified
Slump of Sealants	nil	ASTM D-2202
Rheological, Vertical @ 120°F (49°C)	non-sag	ASTM C-639
Volatile Organic Content:	2.58 % by wt. 29 g/L 0.25 lbs/gal	
Service Temperature	-80°F to 350°F -62.2°C to 176.6°C	

*Requires Technical Service Approval
For Structural Glazing Installations

Test results are averages obtained under laboratory conditions. Reasonable variations can be expected.

PACKAGING

- 10.1 fl. oz. (300 ml) disposable cartridges
- 600 ml sausage packs
- 2 gal (7.5 L) pail
- 52 gal (197 L) in 55 gal drum

Special packaging available upon request – ask your local Representative for more information.

STORAGE/SHELF LIFE

When stored in the original, unopened containers at or below 90°F (32°C), shelf life is one year. A product skin may form in pails and drums, remove prior to use.

COLORS

Adobe Tan, Almond, Aluminum, Beige, Black, Bronze, Colonial White, Dusty Rose, Gray, Hartford Green, Ivy Green, Limestone, Medium Bronze, Quarry Red, Sandstone and White. Custom colors are available upon request - ask your local Representative for more information.

EXPANSION JOINT DESIGN

1. The number of joints and the joint width should be designed for a maximum of $\pm 50\%$ movement of joint width at time of installation.
2. The depth of the sealant should be 1/2 the width of the joint. The maximum depth is 1/2 inch (13mm) and the minimum is 1/4 inch (6mm).
3. To control joint depth, use closed cell polyethylene, non-gassing polyolefin or open cell polyurethane backer rod. If joint depth does not allow for backer rod, use polyethylene bond breaker tape to prevent three-sided adhesion.
4. Closed cell backer rod should be 25% larger than joint width; do not compress more than 40%. Open cell should be compressed 40%.
5. Do not use open cell rod in horizontal on grade joint or with E.I.F.S.
6. When installing during time of large temperature swings such as spring or fall, and in joints designed for movement greater than $\pm 25\%$, be aware of the significant joint movement before cure, that may cause aesthetic issues such as ripples in the sealant surface. Performance will not be affected.

SURFACE PREPARATION

The substrate must be clean, dry, frost free, sound and free of any oils, greases or incompatible sealers, paints or coatings that may interfere with adhesion.

POROUS SUBSTRATES – clean by mechanical methods to expose a sound surface free of contamination and laitance.

NON-POROUS SUBSTRATES – for cleaning non-porous substrates, use two cloth wipe method using xylene or an approved commercial solvent. Allow solvent to evaporate prior to sealant application.

PRIMING

BONDAFLEX Sil 295 is designed to obtain adhesion without the use of a primer; however, certain substrates may require a primer. Test by applying the sealant and/or primer sealant combination to confirm results and proposed application methods. Refer to Technical Data Sheet for primers **BONDAFLEX Sil 2000**, **BONDAFLEX Sil 2100**, **BONDAFLEX Sil 2300** or **BONDAFLEX MP 1500** and contact Technical Service for additional information.

APPLICATION

Expansion Joint

1. Ready to use, apply using professional caulking gun. Do not open product container until preparation work has been completed.
2. Apply sealant using consistent, positive pressure to force sealant into the joint.
3. Tool sealant to create a concave joint shape and maximum adhesion. Dry tooling is recommended. **DO NOT** use soapy water or other liquids when tooling.

CLEAN UP

Remove excess sealant from substrate while uncured using a commercial solvent, such as xylene. Cured sealant may be removed by mechanical means.

LIMITATIONS

- Do not allow sealant to come in contact with solvent during cure.
- Do not allow sealant to come in contact with curing polyurethane sealants during cure.
- Not intended for water immersion.
- Sealant may be applied below freezing temperatures if substrates are completely dry, frost free and clean. Contact Technical Service for more information.
- Do not apply when substrate temperatures are below -20°F or above 130°F.
- For structural glazing applications without prior approval: contact May National Associates for technical recommendations.


- Not recommended for horizontal vehicular traffic.
- Do not apply to surfaces that will be painted, as sealant is not paintable.
- Do not apply to substrates that bleed oil, plasticizers or solvent.
- Do not apply to damp or wet substrates.
- Lower temperature and humidity will extend tack free and cure rates.
- Allow treated wood to age six months before application.
- Brass and copper may be discolored. Test apply prior to application.
- Test sensitive substrates, such as mirror backings for compatibility before use.

FIRST AID

In case of eye contact, flush thoroughly with water for at least 15 minutes. **SEEK IMMEDIATE MEDICAL ATTENTION.** In case of skin contact, wash affected areas with soap and water. If irritation persists, **SEEK MEDICAL ATTENTION.** Remove and wash contaminated clothing. If inhalation causes physical discomfort, remove to fresh air. If discomfort persists or any breathing difficulty occurs or if swallowed, **SEEK IMMEDIATE MEDICAL ATTENTION.** Refer to Material Safety Data Sheet (MSDS) for further information.

PRECAUTIONS

KEEP OUT OF THE REACH OF CHILDREN. Use only with adequate ventilation. Keep container closed. Prevent contact with skin, eyes and clothing. Wash thoroughly after handling. **DO NOT** take internally. Use impervious gloves, eye protection and if the TLV is exceeded or used in a poorly ventilated area, use NIOSH/MSHA approved respiratory protection in accordance with applicable federal, state and local regulations.



SEALANT · WATERPROOFING & RESTORATION INSTITUTE

Issued to: **May National Associates, Inc.**

Product: Bondaflex Sil 295 Silicone Construction Sealant

C719: Pass ✓ **Ext: +50%** **Comp: -50%**

Substrate: Glass, Aluminum, Mortar
(Mortar substrates primed with SIL 2000 Primer.)

C661: Rating 15

Validation Date: 12/19/05 - 12/18/10

No. 1205-2951210 Copyright © 2005

SEALANT VALIDATION
www.swrionline.org

May National Associates, Inc.
995 Towbin Ave.
Lakewood, NJ 08701

Ph: 800-641-0234
Fax: 973-473-4222
www.bondaflex.com

MAY NATIONAL ASSOCIATES, INC. (MNA) PRODUCTS ARE WARRANTED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET MNA'S PUBLISHED TYPICAL PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH MNA'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND MNA'S STANDARDS. SHOULD THERE BE MANUFACTURING DEFECTS OF ANY KIND, THE EXCLUSIVE REMEDY OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID, TO MNA FOR REPLACEMENT. THERE IS NO OTHER WARRANTY, EITHER EXPRESS OR IMPLIED, RELATING TO THE GOODS BEING SOLD, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. MNA'S LIABILITY IS LIMITED TO REPLACEMENT OF DEFECTIVE MATERIAL AND MNA SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, CONSEQUENTIAL, INCIDENTAL OR REMOTE DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR FROM ANY OTHER CAUSE WHATSOEVER, REGARDLESS OF LEGAL THEORY.