



USAGE TABLES

SUBSTRATE

This table is prepared to assist the user in selecting a product that will adhere to a commonly used substrate without priming. Adhesion is based on a properly cleaned and prepared substrate. Substrates not listed, questionable or not previously tested should be pre-tested prior to use. Adhesion may be enhanced by the use of primers. Pre-application adhesion test is recommended prior to job start-up. This will be evaluated preparation and application under actual job conditions. Reference Application Manual for testing procedures.

	Acrylic FRP	Aluminized Steel	Aluminum	Brick/Masonry	Common Woods**	Concrete/Mortar	EIFS	Fiberglass	Fluoropolymer Painted Surface	Galvanized	Glass	Granite		Other Natural Stones	Polyester Powder Coating	PVC	Standard Drywall	Steel	Tile & Ceramics	
PUR 2 NS	X		X	X	X	X	X	X	X	X	X	X	PUR 2 NS	X	X		X	X	X	PUR 2 NS
PUR 2 SL	X		X	X	X	X	X	X	X	X	X	X	PUR 2 SL	X			X	X	X	PUR 2 SL
PUR 25	X		X	X	X	X	X	X	X	X	X	X	PUR 25	X	X		X	X	X	PUR 25
PUR 25 Tex	X		X	X	X	X	X	X	X	X	X	X	PUR 25 Tex	X			X	X	X	PUR 25 Tex
PUR 35 SL	X		X	X	X	X	X	X	X	X	X	X	PUR 35 SL	X			X	X	X	PUR 35 SL
PUR 40 FC	X	X	X	X	X	X	X	X	X	X	X	X	PUR 40 FC	X	X	X	X	X	X	PUR 40 FC
PUR 50 FC	X	X	X	X	X	X	X	X	X	X	X	X	PUR 50 FC	X	X	X	X	X	X	PUR 50 FC
PUR 60 FC	X	X	X	X	X	X	X	X	X	X	X	X	PUR 60 FC	X		X	X	X	X	PUR 60 FC
PUR 80	X		X	X	X	X	X	X	X	X	X	X	PUR 80	X	X	X	X	X	X	PUR 80
STP 25	X		X	X	X	X	X	X	X	X	X	X	STP 25	X		X	X	X	X	STP 25
STP 35	X		X	X	X	X	X	X	X	X	X	X	STP 35	X		X	X	X	X	STP 35
STP SPRAYABLE	X	X	X	X	X	X	X	X	X	X	X	X	STP SPRAYABLE	X		X	X	X	X	STP SPRAYABLE
SIL 100 GP			X		X			X			X	X*	SIL 100 GP	X*				X	X	SIL 100 GP
SIL 100 HT			X		X			X			X	X*	SIL 100 HT	X*					X	SIL 100 HT
SIL 100 WF			X		X			X			X	X	SIL 100 WF	X					X	SIL 100 WF
SIL 100 GC			X		X			X			X		SIL 100 GC						X	SIL 100 GC
SIL 150			X	X	X	X	X	X			X		SIL 150				X		X	SIL 150
SIL 200 GPN	X	X	X	X	X	X	X	X	X	X	X	X*	SIL 200 GPN	X*		X	X		X	SIL 200 GPN
SIL 200 SL	X		X	X	X	X		X	X	X	X	X*	SIL 200 SL	X*		X	X		X	SIL 200 SL
SIL 211	X	X	X	X	X			X	X	X	X	X*	SIL 211	X*	X	X	X	X	X	SIL 211
SIL 201 FC	X	X	X	X	X			X	X	X	X	X*	SIL 201 FC	X*	X	X	X	X	X	SIL 201 FC
SIL 290	X	X	X	X	X	X	X	X	X	X	X	X*	SIL 290	X		X	X		X	SIL 290
SIL 295	X	X	X	X	X	X	X	X	X	X	X	X	SIL 295	X	X	X	X		X	SIL 295
SILBRIDGE 300	X	X	X	X	X	X	X	X	X	X	X	X	SILBRIDGE 300	X	X	X	X		X	SILBRIDGE 300
SIL 728 NS			X	X	X	X					X	X	SIL 728 NS	X*					X	SIL 728 NS
SIL 728 SL			X	X	X	X					X	X	SIL 728 SL	X*					X	SIL 728 SL
SIL 728 SG			X	X	X	X					X	X	SIL 728 SG	X*					X	SIL 728 SG
SIL 728 RCS			X	X	X	X					X	X	SIL 728 RCS	X*					X	SIL 728 RCS
600 ACRYLIC LATEX			X	X	X	X					X		600 ACRYLIC LATEX	X			X		X	600 ACRYLIC LATEX
SIL-A 700			X	X	X	X					X		SIL-A 700	X			X		X	SIL-A 700

* MAY CAUSE STAINING

** DOES NOT INCLUDE PRESSURE TREATED AND WOODS THAT EXUDE OILS OR TANNINS; SUCH AS TEAK, MAHOGANY AND RED WOOD